



Era Polymers Pty. Ltd.
2-4 Green Street, Banksmeadow
Sydney, NSW 2019
AUSTRALIA
www.erapol.com.au

Eracat MFD

POLYURETHANE CATALYST

TECHNICAL DATASHEET

Eracat MFD is a proprietary catalyst recommended for the production of polyurethane elastomers where maximum reaction control is required. **Eracat MFD** provides a reduced toxicity alternative to catalysts based on mercury without sacrificing performance.

Product Specification

Appearance	Clear to yellowish liquid
Boiling Point (°F)	388
Flash Point (°F)	198
Specific Gravity at 77°F	0.99

Mixing Ratio

The quantity of **Eracat MFD** determines the pot life (gelation) and is normally within the range **0.40 – 0.60 parts per hundred** based on the total weight of the system. **Eracat MFD** is normally incorporated into the polyol or curative side.

Please consult Era Polymers for further information on catalyst levels.

Handling

Keep away from air and protect against heat, light and humidity.

Consult the Material Safety Data Sheet for further safety information.



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.