

SYDNEY

25 – 27 Green St
East Botany, NSW 2019
Ph: +61 2 9666 3788
Fax: +61 2 9666 4805

MELBOURNE

29 Trade Place
Vermont, VIC 3133
Ph: 03 9872 4033
Fax: 03 9872 4099

BRISBANE

Unit 6/5 Deakin Street
Brendale, QLD 4500
Ph: 07 3205 8510
Fax: 07 3205 9616

SINGAPORE

H.K. Moey
9 Elias Terrace
Singapore 519772
Ph: +65 6582 8103
Fax: +65 6584 8100
Mobile: +65 9751 0026



TECHNICAL DATA

Greenlink EF507

*HIGH PERFORMANCE POLYESTER BASED URETHANE
MOULDING FOAM*

Greenlink EF507 is a high resilient and abrasion resistant elastomeric polyurethane foam. Apart from abrasion and impact resistance, they offer exceptional cut and tear resistance as well as a high degree of chemical and oil resistance. This combination of properties means that this foam is suitable for such arduous applications as pipeline pigs and automotive bump-stops.

The system can be manually drill mixed (@ a minimum speed of 2000rpm), however, it is preferable to process through plural component polyurethane dispensing machine.

COMPONENT PROPERTIES

	Isocyanate	Polyol
Appearance	Opaque	Opaque
Viscosity (cps)	910 ± 50 @ 30°C	1700 ± 100 @ 40°C
Specific Gravity	1.12 @ 30°C	1.17 @ 40°C

REACTION PROFILE

Laboratory results based on hand-mix.

Mix ratio by weight (Polyol : Iso)

100 : 125

Temperature of Polyol (°C)	35 – 40
Temperature of Isocyanate (°C)	25 – 30
Mould Temperature (°C)	50 – 60
Mix Time (seconds)	7
Cream Time (seconds)	13
Gel Time (seconds)	31
Tack-Free Time (seconds):	105
Free Rise Density (kg/m³)	145
Demould Time (minutes) *	10

* Demould time is based on laboratory results of a sample size 100-200g of moulded foam. Demould time is dependent on process temperatures for components, mould temperature, mass of material mixed and whether it is hand or machine processed.

Properties presented above are to be used as a guide only and are not intended for specification purposes.

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.



SYDNEY

25 – 27 Green St
East Botany, NSW 2019
Ph: +61 2 9666 3788
Fax: +61 2 9666 4805

MELBOURNE

29 Trade Place
Vermont, VIC 3133
Ph: 03 9872 4033
Fax: 03 9872 4099

BRISBANE

Unit 6/5 Deakin Street
Brendale, QLD 4500
Ph: 07 3205 8510
Fax: 07 3205 9616

SINGAPORE

H.K. Moey
9 Elias Terrace
Singapore 519772
Ph: +65 6582 8103
Fax: +65 6584 8100
Mobile: +65 9751 0026

MIXING PROCEDURES

To produce high quality foam it is essential that the following procedures be carefully followed.

1. The Polyol should be **accurately** weighed. Suitable containers include metal or plastic. Ensure that the containers are clean and dry.

Note: the polyol is a blend of different components and should be mechanically stirred before removing material from the drum.

2. The Isocyanate should then also be **accurately** weighed into the same container. The reaction between the two products essentially begins immediately when the two products meet.

3. The mixture should be mixed with an electric drill to which a paint mixer has been attached. It is essential that the drill is capable of mixing at least at 2000 rpm. A slower speed will produce poor quality foam.

4. The mixture should be mixed for typically about 7 seconds. The mixing time will depend on a variety of factors including:

- **Cream time of the material:** The mixture should be mixed and poured into the mould before the cream time has been reached.
- **The temperature of the Polyol/Isocyanate:** If ambient and chemical temperatures are too high then the cream time is much faster.
- **Batch size:** Generally a larger batch size will react faster than a smaller batch.

MOULD TEMPERATURE

Ideally the mould temperature should be 20°C HIGHER than the chemical temperature. Therefore if the chemical temperatures are 35°C then the mould temperature will be 50-60°C.

MOULDS

a. FABRICATION

Moulds can be fabricated from a variety of substances including metal, plastics, fiberglass and timber. A mould release, such as Eralease must be used before each moulding.

b. CONDITIONING

When using a new mould, some release agent conditioning of the mould surface maybe necessary. To do this, 2-3 coats of release agent should be applied one after another, with sufficient time between each coat to allow for solvent evaporation.

c. VENTING

These elastomeric foams generate pressure inside a mould. It is important therefore to incorporate a few small (about 1 mm) vent holes in the mould. This will allow contained air and gas to escape. It is important however, to only allow a minimal amount of material to escape. If a large amount escapes either through the vent holes or through the part line of the mould, then this effect will produce large holes near the escape point.

d. POSITIONING OF MOULD

If a void free space is required it may be necessary to angle the mould in such a way that the air vents are at the highest point.

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

Era Polymers Pty. Ltd.

A.B.N. 14 003 055 936

erapol@erapol.com.au
www.erapol.com.au

SYDNEY

25 – 27 Green St
East Botany, NSW 2019
Ph: +61 2 9666 3788
Fax: +61 2 9666 4805

MELBOURNE

29 Trade Place
Vermont, VIC 3133
Ph: 03 9872 4033
Fax: 03 9872 4099

BRISBANE

Unit 6/5 Deakin Street
Brendale, QLD 4500
Ph: 07 3205 8510
Fax: 07 3205 9616

SINGAPORE

H.K. Moey
9 Elias Terrace
Singapore 519772
Ph: +65 6582 8103
Fax: +65 6584 8100
Mobile: +65 9751 0026

POST CURE

Greenlink EF507 will continue to cure at room temperature after demould time and the maximum physical properties will develop at room temperature after a week. This applies to "summer" temperatures. Ambient winter temperatures of 10 - 15°C will unacceptably retard the rate of cure; therefore a "post cure" would be desirable under these conditions. A suggested post cure would be 1- 2 hours at 50 - 60°C.

NOTE: The foam, when de-moulded, will be "green". It should therefore be carefully handled so as to not introduce a permanent set.

HANDLING OF RAW MATERIALS

EF507 ISO

EF507 Iso is an MDI prepolymer. It is liquid at room temperature, hence:

1. Store in a dry environment, i.e. exclude moisture by blanketing with nitrogen.
2. Store between 20 - 35°C. If the temperature falls below 20°C, the product may crystallise.
3. As with all isocyanates, good industrial practice should be employed, e.g. avoid contact with eyes, skin and clothing. Avoid breathing in vapours. Please consult Material Safety Data Sheet for further instructions.

EF507 POLYOL

EF507 Polyol presents no particular health hazards.

NOTE: The polyol may separate with time - it is suggested that the entire contents be stirred thoroughly before decanting.

NOTE: The polyol may solidify if the temperature drops below 15°C. Heating to 50°C will re-melt the polyol.

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

Version: 1

Date of Issue: 14/9/2005

Page 3 of 3
Greenlink EF507

