

SYDNEY

25 – 27 Green St
East Botany, NSW 2019
Ph: +61 2 9666 3788
Fax: +61 2 9666 4805

MELBOURNE

29 Trade Place
Vermont, VIC 3133
Ph: 03 9872 4033
Fax: 03 9872 4099

BRISBANE

Unit 6/5 Deakin Street
Brendale, QLD 4500
Ph: 07 3205 8510
Fax: 07 3205 9616

SINGAPORE

H.K. Moey
9 Elias Terrace
Singapore 519772
Ph: +65 6582 8103
Fax: +65 6584 8100
Mobile: +65 9751 0026



TECHNICAL DATA
Greenlink PFA170

PANEL FOAM ADHESIVE

Greenlink PFA170 is a two-pack polyurethane panel foam adhesive system with a free rise density of 38 kg/m³.

The system is designed to bond metal sheeting to polystyrene in a continuous panel forming process. Erathane PFA170 is also tolerant to process fluctuation and is compatible with various plural component dispensing equipment.

Such equipment includes low-pressure plural component polyurethane dispensers or the traditional gravity fed 'drip and smear' panel process.

COMPONENT PROPERTIES

	Polyol	Isocyanate
Appearance	Clear, yellow liquid	Brown liquid
Brookfield Viscosity (cps)	525	200
Specific Gravity	1.08	1.23

REACTION PROFILE

Laboratory results based on hand-mix @ 20°C

Mix Ratio Range by Weight (Polyol: Iso)	100:170	100:180
Mix time (seconds)	8	8
Cream time (seconds)	11	11
Gel time (seconds)	32	34
Tack free time (seconds)	45	46
Free rise density (kg/m³)	37	38

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.



SYDNEY

25 – 27 Green St
East Botany, NSW 2019
Ph: +61 2 9666 3788
Fax: +61 2 9666 4805

MELBOURNE

29 Trade Place
Vermont, VIC 3133
Ph: 03 9872 4033
Fax: 03 9872 4099

BRISBANE

Unit 6/5 Deakin Street
Brendale, QLD 4500
Ph: 07 3205 8510
Fax: 07 3205 9616

SINGAPORE

H.K. Moey
9 Elias Terrace
Singapore 519772
Ph: +65 6582 8103
Fax: +65 6584 8100
Mobile: +65 9751 0026

HANDLING OF RAW MATERIALS

PFA170 Isocyanate

1. Store in a dry environment; i.e. exclude moisture by blanketing with nitrogen.
2. Store between 20 - 35°C. If the temperature falls below 18°C, the system will react slower extending the reaction profile.
3. As with all isocyanates, good industrial practice should be employed e.g. avoid contact with eyes, skin and clothing. Avoid breathing in vapours.

PFA170 Polyol

1. Store in a dry environment between 20 - 35°C. If the temperature falls below 18°C, the system will react slower extending the reaction profile.
2. Consult the MSD's for the system for specific Health and Safety details.

This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.