



Era Polymers Pty. Ltd.
2-4 Green Street, Banksmeadow
Sydney, NSW 2019
AUSTRALIA
www.erapol.com.au

Erapol L-RN71A

HIGH PERFORMANCE POLYESTER POLYURETHANE

TECHNICAL DATASHEET

Erapol L-RN71A is an isocyanate-terminated polyester based urethane prepolymer. It is formulated for use with MOCA curative.

Application

Erapol L-RN71A elastomers provide properties generally not available with rubbers, plastics or metals. They show improved solvent and oil resistance and better thermal stability than most general-purpose rubbers and plastics. Other outstanding properties include high abrasion and tear resistance, excellent load-bearing capacity, toughness and resiliency.

Product Specification

% NCO	2.50 ± 0.25
Viscosity at 80°C (176°F) (cps)	1700 – 2500
Color	Clear, light amber

Mixing and Curing Conditions

		L-RN71A
Erapol L-RN71A	(pph)	100
MOCA level	(pph)	7.6
Recommended % Theory		95
Erapol Temperature	°F (°C)	167 - 185 (75 - 85)
Curative Temperature	°F (°C)	230 – 248 (110 – 120)
Pot Life *	(mins)	4 – 6
Demold Time at 212°F (100°C) **	(mins)	45
Post Cure Time at 212°F (100°C)	(hrs)	16

* Pot life based on a 200g sample, prepolymer at 176°F (80°C), MOCA at 230°F (110°C), Eracure 300 and Eracure 110 at 77°F (25°C).

** Demold time based on a 200g rectangular slab. Demold time will depend on the size and shape of the cast part, the mold temperature and the curing temperature.



This information is of general nature and is supplied without recommendation or guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.

Physical Properties

Properties presented below are to be used as a guide and not intended for specification purposes.

		L-RN71A	TEST METHOD
Hardness, cured at 176°F (80°C)	(Shore A)	76	ASTM D2240
Hardness, cured at 212°F (100°C)	(Shore A)	71	ASTM D2240
Tensile Strength	psi (MPa)	5743 (39.6)	ASTM D412
100% Modulus	psi (MPa)	406 (2.8)	ASTM D412
300% Modulus	psi (MPa)	1059 (7.3)	ASTM D412
Elongation	(%)	760	ASTM D412
Tear Strength, Die C	pli (kN/m)	336 (59)	ASTM D624
DIN Resilience	(%)	45	DIN 53512
DIN Abrasion Resistance 10N	(mm ³)	81	ASTM D5963
Cured Specific Gravity	(g/cm ³)	1.24	ASTM D1817

Processing Procedure

1. Heat pre-weighed amounts of **Erapol L-RN71A** to 176 – 212°F (80 – 100°C) and degas at -95kPa of vacuum until excessive bubbling stops. Containers should be unlined metal, plastic or glass and should be large enough to allow for foaming during degassing.
2. MOCA must be melted at 248°F (120°C) prior to mixing. After adding curative, mix thoroughly and degas at -95kPa for 1 to 2 minutes.
3. Pour mixed system into molds, preheated to 212°F (100°C), which have been coated with **Salease** mold release or equivalent.
4. Cure in accordance with above recommendations.

Adhesion

Adhesion of Erapol based elastomers to various substrates is at best marginal if a primer is not used. Please consult Era Polymers for specific recommendations to improve adhesion.

Handling Precautions

Consult the product's material safety data sheet (MSDS) for specific hazard and handling information before use. **Erapol L-RN71A** contains small amounts of free TDI. Therefore the product should be used in well-ventilated areas. Avoid breathing in vapors and protect skin and eyes from contact.

In case of skin contact, immediately remove excess, wash with soap and water. For eye contact, immediately flush with water for at least 15 minutes.

If nose, throat or lungs become irritated from breathing in vapors, remove exposed person to fresh air. Call a physician.



This information is of general nature and is supplied without recommendation of guarantee. It does not make claim to be free from patent infringement. Properties shown are typical and do not imply specification tolerances. Era Polymers cannot accept liability for loss or damage through use. Whilst these technical details are based on expert knowledge, practical experience and laboratory testing, successful application depends upon the nature and conditions in which the products are supplied. Users must, by comprehensive testing, evaluate this product in their own application.